

### Sieve Analysis ASTM D 5644

**Product:** Ambient Crumb Rubber 30-50 Mesh  
**Date Tested:** Monday, November 21, 2011  
**Bag ID:** 1131311-1

**Product ID:** 30-50

**Fiber Content:** < 0.1 %  
**Mass (grams):** < 0.1 %

**Sample Weight:** 100 g  
**Talc Weight:** 5 g

ASTM E11 Sieve No.	mm	Weight Retained (g)	Individual % Retained	Cummulative % Passing
18	0.853	0.0	0.0%	100.0%
20	0.841	6.7	6.7%	93.3%
30	0.5	32.9	32.9%	60.4%
40	0.47	20.0	20.0%	40.4%
50	0.297	22.0	22.0%	18.4%
60	0.25	5.5	5.5%	12.9%
70	0.21	4.4	4.4%	8.5%
80	0.177	2.4	2.4%	6.1%
Pan		8.7	6.1%	
<b>Total</b>		<b>102.60</b>	<b>100.0%</b>	

